

Technical Literature F-01-05

Oil Resistance of AURUM[®] JCN3030

Given below are results of an oil resistance test conducted on AURUM[®] JCN3030.

1. Immersion Conditions

Oil:	Nisseki High Therm 32 thermal oil
Temperature:	180°C
Time:	0, 500, 1,000 and 2,000 hrs

2. Sample

Injection-molded articles of JCN3030 (ASTM bending test specimens)

3. Test Results

Time hrs	Flexural strength kg/cm ²	Flexural modulus kg/cm ²	Weigh retention percentage %	Change in appearance Remarks
	32.7	1,810		
	31.7	1,850		
0	31.5	1,880		
	31.7	1,860		
	32.2	1,950		
Average	32.0	1,870	100	
	34.1	1,900		
	33.8	1,920		
500	33.8	1,940		No obongo in
	33.0	1,860		No change in
	32.8	1,900		appearance
Average	33.5	1,900		
Retention (%)	<u>104.7</u>	<u>101.6</u>	<u>99.5</u>	
	33.4	1,840		
	33.1	1,910		
1000	32.9	1,910		No obongo in
	34.2	1,950		No change in
	34.2	1,950		appearance
Average	33.7	1,910		
Retention (%)	<u>105.3</u>	<u>102.1</u>	<u>99.4</u>	

The information contained herein is based on the information and data available at this moment, but none of the data or evaluation results contained herein provide any warranty whatsoever.

MITSUI CHEMICALS, INC.



http://www.mitsuichem.com Shiodome City Center 1-5-2, Higashi-Shimbashi, Minato-ku, Tokyo 105-7117, Japan

2000	34.2 33.7 33.7 33.5 34.0	1,930 1,950 1,980 1,950 1,980		No change in appearance
Average	33.8	1,960		
Retention (%)	<u>105.6</u>	<u>104.8</u>	<u>99.5</u>	

Bending test conditions: CHS = 1.5 mm/min


Oil Resistance of AURUM[®] (180^o) (%)

(Film)

		Gear oil		
		500 hrs	1,000 hrs	2,000 hrs
Retention percentage	Tensile strength at yield point Tensile strength at break	110 95	110 90	120 95
Other	Appearance	No change	No change	No change

Note: Gear oil: Showa White Parrot S-3 (10W-30)

JCN3030 Bending Oil Test



The information contained herein is based on the information and data available at this moment, but none of the data or evaluation results contained herein provide any warranty whatsoever.

MITSUI CHEMICALS, INC.

http://www.mitsuichem.com Shiodome City Center 1-5-2, Higashi-Shimbashi, Minato-ku, Tokyo 105-7117, Japan



The information contained herein is based on the information and data available at this moment, but none of the data or evaluation results contained herein provide any warranty whatsoever.