

Product name	Resin constant value				Room temp. drying		Pencil hardness (7days)	Features	Applications
	NV (%)	Vis (mPa·s/25°C)	pH	AV	Set to touch (min)	Thorough dry (min)			
UD500	38	500~1500	7	25	4	30	B	General purpose	Very quick drying type, General type
UD524	38	100~400	7.5	22.5	6	35	B	Wood floor	Softness
UD350	38	50~500	7	40	7	30	B	PET coating	High acid value
UD600	38	200~700	8.6	25	7 ※ ¹	30 ※ ¹	HB ※ ¹	Wood floor	Air drying type with metal catalysts
UD736	38	50~500	7	30	8 ※ ²	35 ※ ²	2H ※ ²	Wood floor	Cross-lining type with isocyanate

NV: Non-volatile Vis: Viscosity

※¹ with metal catalysts

※² with OLESTER™ XUD 1248NP(isocyanate)